

TYPICAL PROPERTIES OF
Ensolite® IV3

POLYMER

PVC/NBR/CR

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT
COMPRESSION DEFLECTION 25%	ASTM D1056	psi kPa	9- 13 62 - 89.6
DENSITY	ASTM D1056	pcf g/cm ³	7 - 9.5 .112- .152
COMPRESSION SET (MAX)	ASTM D1056	%	35
WATER ABSORPTION (MAX)	ASTM D1056	%	10
TENSILE STRENGTH (MIN)	ASTM D412 (DIE A)	psi kPa	100 690
ELONGATION (MIN)	ASTM D412 (DIE A)	%	100
TEAR STRENGTH (Typical)	ASTM D624 (DIE C)	lb/in kN/m	20 3.5
CD CHANGE AFTER OVEN AGING	ASTM D1056	%	±30
SHORE OO	ASTM D2240		60 - 70
COLOR	N/A	N/A	BLACK

SPECIFICATIONS
ASTM D1056-07.....2B3 ASTM D1056 Suffix's.....B3, C1,F1, M ASTM D6576-07.....Type II A, B, Medium GMW15473.....Class I Type V WSK-M2D419-A.....Type 4 TSM 1501G.....2B3 Contact customer service for exceptions.
FLAMMABILITY SPECIFICATIONS
FMVSS-302.....PASS FAR 25.853 F Part 1 (a)(1)(ii)PASS UL94 HF-1.....LISTED ¹ UL94 V0.....LISTED ¹ ¹ Contact customer service for thickness data.
ADDITIONAL INFORMATION
Service Temperature -40°F to 200°F

For updates to this document, please refer to our website or contact customer service.

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

P.O. BOX 2965 HUNTINGTON, WEST VIRGINIA 25728
TELEPHONE (304) 525-3116 • FAX (304) 523-4316
WWW.RUBBERLITE.COM

Issue Date: 3/5/12

