

POLYMER



847-593-5630

TYPICAL PROPERTIES OF **P493SHD**

<u>EPDM</u>

| PHYSICAL PROPERTY | TEST METHOD | UNIT OF MEASURE | RESULT | SPECIFICATIONS |
|----------------------------|----------------------|--------------------------|---------------------|--|
| COMPRESSION DEFLECTION 25% | ASTM D1056 | psi kPa | 9 - 13 62 - 89.6 | ASTM D1056-072A3 ASTM D1056 Suffix'sB2, C1, F2, M |
| DENSITY | ASTM D1056 | pcf g/cm ³ | 15 .240 | |
| WATER ABSORPTION (MAX) | ASTM D1056 | % | 5 | FLAMMABILITY SPECIFICATIONS FMVSS-302 PASS ADDITIONAL INFORMATION Service Temperature -67 % to 300 % |
| TENSILE STRENGTH (MIN) | ASTM D412 (DIE A) | psi kPa | 110 758.4 | |
| ELONGATION (MIN) | ASTM D412 (DIE A) | % | 200 | |
| COMPRESSION SET (MAX) | ASTM D1056 | % | 25 | |
| CD CHANGE AFTER OVEN AGING | ASTM D1056 | % | ±30 | |
| COLOR | N/A | N/A | BLACK | |

For updates to this document, please refer to our website or contact customer service.

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

P.O. BOX 2965 HUNTINGTON, WEST VIRGINIA 25728 TELEPHONE (304) 525-3116 • FAX (304) 523-4316 WWW.RUBBERLITE.COM



Issue Date: 3/5/12