

AUTOMOTIVE



Ensolite® IG3

- UL 94 5VA, 5VB, V-0, V-1, HF-1 and HBF listed for flame
- PVC / NBR / CR closed cell material manufactured in continuous rolls
- ASTM D 1056-07 2A3 / 2C3 / 2B3 grade product
- ASTM D 6576-07 Type II, Grades A & B, Condition Medium material

Ensolite®

General Information

Armacell Ensolite® IG3: Armacell LLC (Conover, NC Plant) manufactures a black, continuous, closed cell, medium density (7 - 9 lb./ft³) (112 - 144 kg/m³) PVC/NBR/CR rubber product IG3, that meets all the physical property requirements of ASTM D 1056-07 2A3 / 2C3 / 2B3 and SAE J-18 APR2002 2A3 / 2C3 / 2B3. IG3 has excellent resistance to oil and fuel. IG3 meets the requirements of FMVSS-302 at most thicknesses and is listed to UL94 HF-1 at 1.7 - 3.8 mm (0.067" - 0.149"), UL94HBF at 10 mm (0.393"), UL94 V-1 and 5VA at 3.3 mm (0.130") and UL94V-0 at 6.2 mm (0.244") (UL File# QMFZ2.E55798).

Automotive and Industrial Specifications

The following is a list of automotive and industrial specifications that Armacell Ensolite® IG3 has been tested to or can meet. Additional specifications are listed that have a few exceptions. Feel free to suggest other automotive, military or industrial specifications, and a full review will be made.

Source	Specification	IG3	Comments
ASTM	ASTM D1056-07	2A3 / 2C3 / 2B3	Additional (optional) suffixes can be added
ASTM	ASTM D 6576-07	Type II, Grades A & B, Condition Medium	Formerly MILR6130-C
CAL	CAL 117	Pass	Flame resistance
Chrysler	Chrysler MSZ-75 J18	2A3 / 2C3 / 2B3	Additional (optional) suffixes can be added
Chrysler	Chrysler MS JP9-4	Meets at most thicknesses	Flame resistance (horizontal burn rate)
Federal	FMVSS-302	Meets at most thicknesses	Flame resistance (horizontal burn rate). See note 1
Federal	FAR 25.853	Pass at 1/8" and 1/4"	12 Second Vertical Burn Test. (Test report available upon request)
FORD	FORD WSK M2D 419-A	Type 4	See note 2

Automotive and Industrial Specifications (continued)

Source	Specification	IG3	Comments
GM	GM 6086-M	Type IIIA	CD tested at 50% deflection. See note 3
GM	GM 6090-M	(B4A) Meets at most thicknesses	Flame resistance tested per GM 9070-P (horizontal burn rate)
GM	GMN11106	Type IIIA	CD tested at 50% deflection. See note 3
GM	GMW15473	Class I Type V	CD tested at 50% deflection. See note 3
ISO	ISO 6916	2A3 / 2C3 / 2B3	No exceptions
Military	ASTM D 6576-07	Type II, Grades A & B, Condition Medium	Formerly MILR6130-C
SAE	SAE J18 APR2002	2A3 / 2C3 / 2B3	Additional (optional) suffixes can be added
SAE	SAE J369	Meets at most thicknesses	Flame resistance (horizontal burn rate)
SAE	SAE J 1351	Pass, rating 2	Odor specification
Toyota	TSM 1501G	2A3 / 2C3 / 2B3	No exceptions
Toyota	TSM 0500G	Meets at most thicknesses	Flame resistance (horizontal burn rate)
UL	UL94 5VA	5VA UL Listed at 3.3 mm (.130") and higher	Flame resistance specification. (UL file# QMFZ2.E55798). See note 4
UL	UL94 5VB	5VB UL Listed at 3.3 mm (.130") and higher	Flame resistance specification. (UL file# QMFZ2.E55798). See note 4
UL	UL94 V-0	V-0 UL Listed at 6.2 mm (.244") and higher	Flame resistance specification. (UL file# QMFZ2.E55798). See note 4
UL	UL94 V-1	V-1 UL Listed at 3.3 mm (.130") and higher	Flame resistance specification. (UL file# QMFZ2.E55798). See note 4
UL	UL94 HF-1	HF-1 UL Listed at 1.7 mm - 3.8mm (.067" - .149")	Flame resistance specification. (UL file# QMFZ2.E55798). See note 4
UL	UL94 HBF	HBF UL Listed at 10.0 mm (.393")	Flame resistance specification. (UL file# QMFZ2.E55798). See note 4

Note 1: A number of horizontal burn tests can also be listed (GM 6090, BMW, Volvo, etc.). Request additional information.

Note 2: For all FORD WSK M2D 419-A callouts, request full information for each product due to some exceptions with non-tested staining requirements.

Note 3: For all GM 6086-M, GMN11106 & GMW15473 callouts, Armacell (Ensolite®) certifies to the "basic" requirements only. Request additional information for each product. Providing application (interior, exterior or under-hood) and part thickness is helpful.

Note 4: In reference to UL listing: May be used with Armaflex "520" adhesive.

Roll Size Information

Gauge (in)	Gauge (fraction of an inch)	Gauge (mm)	Tolerance (inches)	Tolerance (mm)	Roll Size W (in)	Roll Size L (ft)	Roll Size W (m)	Roll Size L (m)	Comments
0.50	1/2	12.70	0.500 - 0.575	12.70 - 14.61	42	72	1.07	21.95	S1S
1.00	1	25.40	1.000 - 1.200	25.40 - 30.48	42	72	1.07	21.95	S2S
1.25	1-1/4	31.75	1.250 - 1.450	31.75 - 36.83	54	100	1.37	30.48	U, S2S
1.25	1-1/4	31.75	1.250 - 1.450	31.75 - 36.83	54	50	1.37	15.24	U, S2S

S1S = skin 1 side

S2S = skin 2 sides

U = untrimmed



IG3 Continuous Rolls/Sheets (Black)

Physical Properties	Unit	Test Method	Typical Results
Density	kg/m ³	ASTM D 1056	112 - 144
	lb/ft ³	ASTM D 1056	7.0 - 9.0
Hardness, Durometer Shore 00		ASTM D 2240	65 + 10
Compression Deflection (25%)	kPa	ASTM D 1056	144 - 208
	psi	ASTM D 1056	9.0 - 13.0
50% Compression Set (Room temp)	%	ASTM D 1056	≤ 25%
Tensile Strength	kPa	ASTM D 412 (Die A)	690 minimum
	psi	ASTM D 412 (Die A)	100 minimum
Tear Strength	kN/m	ASTM D 624 (Die C)	2.6
	lb/in	ASTM D 624 (Die C)	15
Elongation	%	ASTM D 412 (Die A)	100 minimum
Service Temperature (1)			
Low	°F (°C)	ASTM D 746	-20°F (-28.9°C)
High Continuous	°F (°C)	ASTM D 746	---
High Intermittent (2)	°F (°C)	ASTM D 746	200 °F (93.3°C)
Water Absorption			
Maximum Weight Change	%	ASTM D 1056	< 10%
Fluid Immersion (7 days at 23°C [73.4°F])			
ASTM Ref. Fuel B, Weight Change (%)	%	ASTM D 1056	< 100%
Accelerated Aging (7 days at 70°C [158°F])			
Flexibility (180° bend without cracking)		ASTM D 1056	Pass
Appearance change		ASTM D 1056	None
Change in Compression Deflection	%	ASTM D 1056	± 30%
Combustion Characteristics (3)		Thicknesses	Comments
FMVSS-302			Pass at most thicknesses
FAR 25.853		1/8" (3.18 mm) & 1/4" (6.35 mm)	Pass
UL94			
5VA /		0.130" (3.3 mm) & higher	Listed, UL file# QMFZ2.E55798
V-0		0.244" (6.2 mm) & higher	Listed, UL file# QMFZ2.E55798
HF-1		0.067" - 0.149" (1.7 mm - 3.8 mm)	Listed, UL file# QMFZ2.E55798
HBF		0.393" (10.0 mm) & higher	Listed, UL file# QMFZ2.E55798

ASTM D 1056 designation: 2A3 / 2C3 / 2B3
 SAE J 18 APR2002 designation: 2A3 / 2C3 / 2B3
 ASTM D 6576: Type II, Grades A & B, Condition Medium
 In reference to UL listing: May be used with Armaflex "520" adhesive
 Standard Roll Widths: 54" (1.37 m)
 Maximum Gauge: 1.25" (31.75 mm)

(1) This recommendation is based on polymer type only. For specific application requirements please contact technical service.

(2) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service.

(3) Flammability – This item and any corresponding data refer to typical performance in the specific test indicated and should not be construed to imply this material's behavior in other fire conditions.

NBR – Acrylonitrile Butadiene Rubber

PVC – Polyvinyl Chloride

CR – Chloroprene (Neoprene)

Vertical Flame / 12 Second Burn per FAR 25.853
Appendix F — Part I Test Criteria and Procedures for Showing
Compliance with Sec. 25.853 or Sec. 25.855

Armacell Ensolite® Product #	Min. Thickness	Pass / Fail	Independent Test Lab Report	Test Report ID #	Polymer	ASTM D 1056 Grade	Density lb./ft³	25% CD (psi)
IG3	1/4"	Pass	2/18/10	0133	PVC/NBR/CR	2B3	7 - 9.5	9 - 13
IG3	1/8"	Pass	2/18/10	0132	PVC/NBR/CR	2B3	7 - 9.5	9 - 13

UL File Number for Armacell Ensolite® IG3

UL File Number: QMFZ2.E55798
Plastics – Component [UL94]

		Min.	Flame	H	H	R T I		H	D	
Material Dsg	Color	mm	Class	W	A	Elec	Mech	T	9	T
				I	I		Imp Str	R	5	I

Nitrile Rubber/Polyvinylchloride/Neoprene(NBR/PVC/CR), closed-cell foam with skin, “Ensolite”, furnished as tubes or sheets.

IG3(ad)(ao)	BK	1-7 - 3.8	HF-1	-	-	50	-	50	-	-	-
		10.0	HBF	-	-	50	-	50			
		3.3	V-1, 5VA	-	-	50	-	50			
		6.2	V-0	-	-	50	-	50			

(ad) - May be used with Armaflex “520” adhesive
 (ao) - Density range 0.11 - 0.15 g/cc

UL Yellow Card Listing Verification Online

To obtain verification online:

1. www.ul.com
2. Click on “Certifications”
3. Click on “Company Name” in the general search area
4. Type in “Armacell” & click “Search”
5. 8 (Eight) Armacell file numbers come up (2 belong to Armacell Germany)
 - For Armacell Ensolite® & Monarch® products [Flame / UL94].
Click on QMFZ2.E55798
 - For Armacell Ensolite® products listed to JMST2 [Gaskets & Seals].
Click on JMST2.MH30018 and JMST2.MH10189
 - For Armacell Monarch® products listed to JMLU2 [Gasket Materials].
Click on JMLU2.MH25062

ARMACELL LLC
 TEL: 1 800 866-5638
 FAX: 919 304-3847
info.us@armacell.com
www.armacell.us
 7600 Oakwood Street Extension • Mebane, NC 27302



Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell’s own technical analysis and testing is accurate to the extent of our knowledge and ability, as of date of printing, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information are provided as a technical service and are subject to change without notice.