

TYPICAL PROPERTIES OF  
**RO-12**

POLYMER

NATURAL RUBBER

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT
COMPRESSION DEFLECTION 25%	ASTM D1056	psi kPa	5 – 10 34.4– 68.9
DENSITY	ASTM D1056	pcf g/cm <sup>3</sup>	26 .416
COMPRESSION SET	ASTM D1056	%	15
CD AFTER OVEN AGING	ASTM D1056	%	20
COLOR	N/A	N/A	BLACK

SPECIFICATIONS	
ASTM D1056-78.....	RO-12
ASTM D1056-07.....	1A2
ADDITIONAL INFORMATION	
Service Temperature	-20°F to 160°F

For updates to this document, please refer to our website or contact customer service.

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

P.O. BOX 2965 HUNTINGTON, WEST VIRGINIA 25728  
TELEPHONE (304) 525-3116 • FAX (304) 523-4316  
WWW.RUBBERLITE.COM

Issue Date: 3/5/12

