

Product Data Sheet

PORON® ShockSeal™ Foam: General Industrial Grades (4790-79)

PROPERTY	TEST METHOD	VALUE			
PHYSICAL					
Density, lb. / ft ³ (kg /m ³)	ASTM D 3574-95, Test A	12 (192)	15 (240)	20 (320)	
Tolerance, %		± 10			
Thickness, inches		0.080-0.375	0.125-0.500	0.062-0.188	
(mm)		(2.03-9.53)	(3.18-12.70)	(1.57-4.78)	
Tolerance, %			± 10		
Standard Color (Code)		Black (04)			
Compression Force Deflection, psi	0.2" / min. Strain Rate	1 - 5	2 – 10	4 – 16	
(kPa)	Force Measured @ 25% Deflection	(7- 35)	(14 – 69)	(28 – 110)	
Typical psi (kPa)					
Compression Set, % max	ASTM D 3574-95	5			
	Test D @ 73°F (23°C)				
	ASTM D 3574-95	10			
	Test D @ 158°F (70°C)				
Tensile Strength, Min. psi (kPa),	ASTM D 3574-75 Test E	30 (207)	60 (414)	100 (689)	
Tensile Elongation, % min.	ASTM D 3574-75 Test E	> 145			
Tear Strength, Min. pli (kN/m)	ASTM D 642-91 Die C	5 (0.9)	6 (1.1)	10 (1.8)	
FLAMMABILITY					
Flammability, inches (mm)	MVSS 302 (Pass ≥)	0.250 (6.35)	0.125 (3.18)	0.062 (1.57)	
ENVIRONMENTAL					
Gasketing and Sealing	UL JMST2 (Consisting of UL50E and UL508)	File MH15464			
Water Absorption, % weight gain	ASTM D 570 – 2hr water immersion @ room temperature	Typical Value 10			

Notes:

All metric conversions are approximate.

Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corporation.

The information contained in this Data Sheet is intended to assist you in designing with Rogers' High Performance Foam Materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers PORON Urethane Foams for each application. The Rogers logo, The world runs better with Rogers, ShockSeal and PORON are licensed trademarks of Rogers Corporation. © 2012 Rogers Corporation, All rights reserved. Printed in U.S.A., 0412-PDF, Publication #17-226