



847-593-5630

www.srpco.com

CROSSLINKED POLYETHELENE

TYPICAL PROPERTIES OF Fuzion[™] 4.0

POLYMER

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	TYPICAL PROPERTY	FLAMMABILITY SPECIFICATION
DENSITY	ASTM D3575	pcf Kg/m ³	4 64	FMVSS-302PASS .250" or Thio
COMPRESSION DEFLECTION 25%	ASTM D3575	psi kPa	9 62	
COMPRESSION DEFLECTION 50%	ASTM D3575	psi kPa	21 145	
TENSILE STRENGTH	ASTM D3575	psi	MACHINE - 96 CROSS - 74	ADDITIONAL INFORMATION
ELONGATION	ASTM D3575	%	MACHINE - 186 CROSS - 190	Service Temperature -76 °F to 194 °F Thermal Conductivity .27 Btu-in/hr-Ft ² -
TEAR STRENGTH	ASTM D3575	lb/in	MACHINE - 25 CROSS - 26	
COMPRESSION SET 50%	ASTM D3575	%	14	
THERMAL STABILITY	ASTM D3575	%	2	
COLOR	N/A	N/A	Black /Grey /Natural	

For updates to this document, please refer to our website or contact customer service.

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

P.O. BOX 2965 HUNTINGTON, WEST VIRGINIA 25728 TELEPHONE (304) 525-3116 • FAX (304) 523-4316 WWW.RUBBERLITE.COM



Issue Date: 3/5/12